

FORTISTONE IBA AGGREGATE CAPPING 6F4 SPECIFICATION

IBA Aggregate that is classified as IBA Aggregate Capping must meet the Specification for Highway Works, Series 600: 6F4.



GRADING LIMITS

Gradings are carried out weekly in accordance with BS EN 933-1 and the limits are below.

TABLE 6/5
IMPORTED ONTO
SITE GRADING
REQUIREMENTS
FOR CLASS 6
ACCEPTABLE
EARTHWORKS
MATERIALS

BS sieve size	Cumulative % by mass passing
63 mm	100
31.5 mm	75-99
16 mm	50-90
8 mm	30-75
4 mm	15-60
1.0 mm	0-35
63 micron	0-15

OTHER TEST RESULTS TO BE DECLARED

Other relevant tests are summarised in the table below.


Test	Standard No.
Grading (PSD)	BS 933-1
Fines Content	BS 933-1
Moisture Content	BS 1377-2
pH Level	
Los Angeles Coefficient	BS 1097-2
Dry Density / Optimum Moisture Content	BS EN 13286-4
Water Soluble Sulphate (WSS)	BS 1744-1
Total Sulfur (TS)	BS 1744-1
Acid Soluble Sulphide (ASS)	BS 1744-1


CE MARKING

A CE Mark is not currently required by EU Regulation 305/2011 and the Construction Products Directive, as SHW Series 600:6F4 is not a harmonised European standard.

Spec 002 Fortistone Capping 6F4
Issue 1.1 / July 2021

FORTIS IBA LTD

 2nd Floor, Fryern House
125 Winchester Road,
Chandler's Ford,
Hampshire, SO53 2DR

 023 8027 3750

 info@fortisiba.com

 www.fortisiba.com

